

| | | |
|---------------------------------|---|---------------------------------|
| Veröffentlichungsnummer: | JP4055406 (A) | Auch veröffentlicht als: |
| Veröffentlichungsdatum: | 1992-02-24 | JP2880260 (B2) |
| Erfinder: | MATSUMOTO TETSUHIRO; UEDA TAKASHI; KIOKA MAMORU | |
| Anmelder: | mitsui petrochemical ind | |
| Klassifikation: | | |
| - Internationale: | C08F10/00; C08F4/60; C08F4/654; C08F10/00; C08F4/00; (IPC1-7): C08F4/654; C08F10/00 | |
| - Europäische: | | |
| Anmeldenummer: | JP19900165300 19900622 | |
| Prioritätsnummer(n): | JP19900165300 19900622 | |

[INPADOC Patentfamilie anzeigen](#)

[Liste der Anführungen anzeigen](#)

[Datenfehler hier melden](#)

Zusammenfassung von JP 4055406 (A)

PURPOSE: To obtain the title catalyst providing a polymer having a narrow particle size and high bulk density by adding a liquid Ti compound to a liquid mixture of a halogen-containing Mg compound, an organic OH compound and specific carboxylic esters to give a solid and blending the solid with an organometallic compound.; **CONSTITUTION:** (A) (i) a liquid mixture comprising a halogen-containing Mg compound, an organic hydroxy compound, an organic carboxylic ester shown by formula I ($R¹ is aryl; $R² is 1-5C hydrocarbon) and an organic carboxylic ester shown by formula II ($R¹ is 6-10C hydrocarbon) in the molar ratio of the compound shown by formula I to the compound shown by formula II of 0.1-5 in the total amounts of the compounds shown by formula I and formula II based on the halogen-containing Mg compound of 0.05-3 (molar ratio) is brought into contact with (ii) a liquid Ti compound to give a solid Ti catalyst component having $\text{d}_{50} = 6\text{ }\mu\text{m}$ average particle diameter, which is blended with (B) an organometallic compound to give a catalyst. An olefin is polymerized or copolymerized in the presence of the catalyst.$$$